



Class 8x19

Full Steel Core



8x19S-IWRC Seale



8x19W-IWRC Warrington

Nominal Diameter	Approximate Mass	Minimum Breaking Force Grade 1570/1770 N/mm ²
inch	lbs. /100ft.	lbs.
5/16	16.8	9900
3/8	25.7	14100
7/16	36.1	19200
1/2	48.2	24900
9/16	61.8	31500
5/8	77.1	38800
3/4	94.0	46900

Nominal Diameter	Approximate Mass		Minimum Breaking Force Grade 1570/1770 N/mm ²	
	mm	Kg/100m	lbs. /100ft. *	kN
8	28.0	18.8	44.6	10000
9	35.6	23.9	56.0	12600
10	43.6	29.3	69.5	15600
11	52.8	35.5	83.1	18700
12	62.8	42.2	98.9	22200
13	72.7	48.9	116	26100
14	85.7	57.6	135	30300
16	111	74.6	177	39800
19	172	116	246	55300

* Metric units take precedence, imperial units shown only for convenience.



THE STANDARDS INSTITUTION OF ISRAEL

Wire Rope Works Messilot Ltd.
 Doar Na Bet Shean 10804
 ISRAEL
 tel: ++972-4-6066-333
 fax: ++972-4-6066-237
 e-mail: messilot@messilot.org.il
 June 2011



© Wire Rope Works
 Messilot Ltd.