



Elevator Wire Rope


Class 9x19 Steel Core




9x17S-IWRC Seale



9x19S-IWRC Seale



9x21F-IWRC Filler



9x25F-IWRC Filler

Nominal Diameter		Approximate Mass		Minimum Breaking Force			
inch	mm	lb. /100ft.	Kg/100m	Traction Grade (1370/1770 N/mm ²)		High Strength Grade (1570/1770 N/mm ²)	
				lbs.	kN	lbs.	kN
5/16	8	17.5	26.1	8930	39.7	9460	42.1
3/8	9.5	24.7	36.8	12600	56.1	13400	59.4
7/16	11.1	34.8	51.8	17000	75.4	18000	79.9
1/2	12.7	46.4	69.0	22700	101	24100	107
5/8	15.9	73.9	110	36900	164	39100	174
11/16	17.5	88.0	131	44100	196	46800	208
3/4	19	103	154	52000	231	55100	245
7/8	22	144	215	70700	314	74900	333

Nominal Diameter mm	Approximate Mass		Minimum Breaking Force			
	Kg/100m	lbs. /100ft.	Grade 1370/1770 N/mm ² kN	Grade 1370/1770 N/mm ² lbs.	Grade 1570/1770 N/mm ² kN	Grade 1570/1770 N/mm ² lbs.
8	26.1	17.5	39.7	8900	42.1	9460
9	33.1	22.2	50.3	11300	53.3	12000
10	42.8	28.8	62.3	14000	66.0	14800
11	51.8	34.8	75.4	17000	79.9	18000
12	61.6	41.4	89.8	20200	95.1	21400
13	72.3	48.6	106	23800	112	25200
14	84.0	56.4	126	28200	133	29200
16	110	73.9	164	36900	174	39100
19	154	103	231	52000	245	55100
22	215	144	314	70700	333	74900

* Metric units take precedence, imperial units shown only for convenience.

The information in this brochure was prepared with utmost care but it is for reference only and is subject to change without notice



THE STANDARDS INSTITUTION OF ISRAEL

Wire Rope Works Messilot Ltd.
Doar Na Bet Shean 10804
ISRAEL

tel: ++972-4-6066-333
fax: ++972-4-6066-237
e-mail: messilot@messilot.org.il
110/M/26 – Aug, 2010



© Wire Rope Works
Messilot Ltd.