


# Table 8: 8xK19S Fiber core MasterForm™ Compacted Strands



8xK19S-NFC  
Seale

Nominal diameter	Approximate mass	Minimum breaking Force	
		Traction Grade	High Strength Grade
mm	lbs/100 ft	lbs	lbs
3/8	23	9850	10900
7/16	31	13400	14900
1/2	40	17500	19600
9/16	50	22200	24900
5/8	62	27400	30800
11/16	74	33200	37300
3/4	88	39500	44400
7/8	120	53800	60500
1	156	70300	79200

Nominal diameter	Approximate mass		Minimum breaking force			
	kg/100m	Lbs/100 ft *	Grade 1370/1770 N/mm <sup>2</sup>		Grade 1570/1770 N/mm <sup>2</sup>	
mm			kN	lbs*	kN	lbs *
10	37.0	25	48.4	10880	53.6	12050
11	44.6	30	58.5	13150	65.0	14600
13	61.9	42	81.7	18400	91.3	20500
16	93.2	63	124	27900	139	31200
19	131	88	176	39500	196	44100
22	175	118	234	52600	264	59300
26	244	164	328	73700	369	83000

\* Metric units take precedence, imperial units shown only for convenience.



THE STANDARDS INSTITUTION OF ISRAEL

Wire Rope Works Messilot Ltd.  
Doar Na Bet Shean 10804  
ISRAEL  
tel: ++972-4-6066-333  
fax: ++972-4-6066-237  
e-mail: messilot@messilot.org.il  
June 2011



© Wire Rope Works  
Messilot Ltd.