




Table 3 : Class 8x19 (Fiber Core)




8x19S-NFC
Seale



8x19W-NFC
Warrington



8x21F-NFC
Filler



8x25F-NFC
Filler

Nom. Diameter inch	Approximate Mass lbs/100 ft	Minimum Breaking Force		
		Iron Grade lbs	Traction Grade lbs	Extra High Strength Grade lbs
5/16	14	2900	5600	6900
3/8	20	4200	8200	9900
7/16	28	5600	11000	13500
1/2	36	7200	14500	17500
9/16	46	9200	18500	22100
5/8	57	11200	23000	27200
11/16	69	13400	27000	32800
3/4	82	16000	32000	38900
13/16	96	18600	37000	46000
7/8	111	21400	42000	52600
15/16	127	24600	48000	60000
1	145	28000	54000	68400

Nominal Diameter mm	Approximate Mass		Minimum Breaking Force			
	kg/100m	lbs/100 ft *	Grade 1370/1770 N/mm ²		Grade 1570/1770 N/mm ²	
			kN	lbs *	kN	lbs *
8	21.8	14.6	28.1	6320	30.8	6920
10	34.0	22.8	44.0	9890	48.1	10800
11	41.1	27.6	53.2	12000	58.1	13100
13	57.5	38.6	74.3	16700	81.2	18300
16	87.0	58.5	113	25400	123	27700
19	123	82.7	159	35700	173	38900
22	165	111	213	47900	233	52400

* Metric units take precedence, imperial units shown only for convenience.



Wire Rope Works Messilot Ltd.
Doar Na Bet Shean 10804
ISRAEL
tel: ++972-4-6066-333
fax: ++972-4-6066-237
e-mail: messilot@messilot.org.il
June 2011



© Wire Rope Works
Messilot Ltd.