



Table 5: Class 8x19 Combined Steel & PP Core



8x19S-IWRC
Seale
8x7+PP Core



8x19W-IWRC
Warrinton
8x7+PP Core

Nominal diameter inch	Approximate mass lbs/100 ft	Minimum breaking Force lbs
5/16	17.3	8650
3/8	24.6	12350
7/16	33.3	16700
1/2	43.3	21700
9/16	54.6	27400
5/8	67.3	35000
3/4	96.6	48400

Nominal diameter mm	Approximate mass		Minimum breaking force	
	kg/100m	lb/100ft *	kN	lb. *
8	25.8	17.3	40.3	9050
9	32.9	22.1	51.0	11450
10	40.3	27.1	63.0	14150
11	48.8	32.8	76.2	17150
12	57.6	38.7	90.7	20400
13	67.1	45.1	106	23800
14	79.0	53.1	124	27900
15	88.9	59.7	142	31900
16	102	68.5	161	36200
18	128	85.9	204	45900
19	143	96.4	227	51000

* Metric units take precedence, imperial units shown only for convenience.



Wire Rope Works Messilot Ltd.
Doar Na Bet Shean 10804
ISRAEL
tel: ++972-4-6066-333
fax: ++972-4-6066-237
e-mail: messilot@messilot.org.il
June 2011



© Wire Rope Works
Messilot Ltd.